

TOP GLOVE

TOP QUALITY, TOP EFFICIENCY

THE WORLD'S LARGEST MANUFACTURER OF GLOVES

NITRILE GLOVE

POWDERED & POWDER - FREE



Functional Benefits

- Protection from unwanted and dangerous substances
- Beaded cuff ensures easy donning and prevent roll down
- Superior strength with better puncture resistance
- Full textured enhances wet and dry grip
- Thinner gauger improves tactile sensitivity
- Custom design enhances comfort and fit
- Provide an alternative solution for individuals who are allergic to natural rubber latex



Nitrile Glove

NITRILE GLOVE

POWDERED & POWDER-FREE

Quality Standards

- Conforms to ASTM D6319 and EN455 Standards
- Manufactured under QSR (GMP), ISO9001 : 2015 and ISO13485 : 2016 Quality Management System
- Biocompatibility tested
- Manufactured from 100% nitrile latex (Acrylonitrile-butadiene)
- Resists permeation by a wide range of chemicals as compared to natural rubber latex of the same thickness
- Conforms to MDD 93/42/EEC Class I

Glove Sizes

- Extra- small, Small, Medium, Large, Extra- large
- Marked in the check box the shipping carton with black ink

Product Specifications

Type	: Powdered & Powder - free; non sterile
Material	: Synthetic Nitrile Latex
Design & Features	: Ambidextrous; textures; beaded cuff; natural white or coloured (blue/green/pink/light purple/black/red)
Storage	: The gloves shall maintain their properties when stored in a cool and dry condition
Shelf-life	: 5 years from date of manufacturing

Physical Dimensions

DIMENSIONS	STANDARDS		
	Top Glove	ASTM D6319	EN 455
Length (mm)	240 min	220 min (size XS, S) 230min (size M, L, XL)	240 min
Width (mm)			
• Extra - small	76 ± 3	70 ± 10	≤80
• Small	84 ± 3	80 ± 10	80 ± 10
• Medium	94 ± 3	95 ± 10	95 ± 10
• Large	105 ± 3	110 ± 10	110 ± 10
• Extra - large	113 ± 3	120 ± 10	≥110
Thickness- Single Wall (mm)			
• Fingers	0.05 min	0.05 min	N/A
• Palm	0.05 min	0.05 min	

Physical Properties

Property	ASTM D 6319	EN 455
Elongation at break (%)		
• Before Aging	Min 500	N/A
• After Aging	Min 400	
Tensile Strength (Mpa)		
• Before Aging	Min 14	N/A
• After Aging	Min 14	
Force at Break (N)		
• Before Aging		6.0
• After Aging	N/A	6.0



International Quality Certificate Awarded :



CE 0321



*EN 374-1 : 2003 *EN374-2 : 2003



* This product is suitable for food handling, excluding acidic food stuff for 2 hours at 40°C (EU No.10/2011).

DP080518/TCT

Connect With Us



سوماتكو
SOMATCO
www.somatco.com

